











UV and chemical resistance



Technical Information































Diameter	Weight	Minimum Strength Spliced Rope	Minimum Strength ISO Unspliced Rope
mm	kg/100m	kg	kg
10	6.5	9,000	10,000
11	7.3	11,000	12,200
12	9.6	12,500	13,900
14	11.0	14,000	15,600
16	15.0	18,400	20,400
18	20.5	24,200	26,900
22	30.6	33,500	37,200
24	39.4	44,000	48,900
26	41.3	46,100	51,200
28	48.6	54,400	60,400
30	58.8	65,800	73,100
32	64.5	72,100	80,100
34	73.6	79,400	88,200
36	82.0	91,600	101,800
40	92.2	103,000	114,400
44	99.1	113,000	125,600
48	144.1	152,000	168,900
52	167.6	165,000	183,300

Diameter, weight and MBS are determined in accordance with CI1500-02. Custom size and length available by request.

























Optima 4S Elongation



OPTIMA 4S



- UHMWPE/UHMWPE
- · Very high strength, firm and round torque free
- Superior wear resistance and durability
- Smooth, reducing frictional heat buildup
- More lighter, floating

OPTIMA 4C



- Polyester/UHMWPE
- Very high strength, firm and round torque free
- High wear resistance and durability
- Offers improved grip



STRENGT













