

T21

Extra Line Double Braid Mooring Line



This Polyester Double Braid Mooring Line is constructed with 12 strand-strand ropes. With a tough, non-twisted Construction and a soft yet solid profile, this rope offers excellent handling characteristics and is well suited for use by boat captains and in towing applications.



Can be certified by



ROPERS
RELIABLE TO THE CORE

TECHNICAL INFORMATION



CORE | Polyester

COVER | Polyester

SPECIFIC GRAVITY | 1.38

CONSTRUCTION | Double Braided

MELTING POINT | 482°F (250°C)

CRITICAL TEMP | 350°F (177°C)

ELONGATION AT 30% BREAK | 7.1%

WATER ABSORPTION | 0.1-0.3%



100% high-strength polyester



Ultra-durable double braid



Outperforms polypropylene, polyethylene and nylon ropes in heat-resistance



Low elongation

Diameter		Weight		Minimum Strength ISO Unspliced Rope	
mm	inch	kg/100m	lbs/100ft	kgf	lbs
22	7/8	41.3	27.7	8,900	19,600
24	1	49.6	33.3	10,600	23,200
26	1 1/16	58.0	38.9	12,300	27,100
28	1 1/8	66.0	44.3	13,900	30,600
30	1 1/4	75.0	50.3	15,600	34,200
38	1 1/2	108.5	72.8	22,400	49,300
40	1 9/16	134.5	90.2	27,000	59,400
42	1 5/8	146.0	97.9	29,400	64,800
44	1 3/4	167.5	112.3	34,700	76,200
50	2	210.0	140.8	41,600	91,400
55	2 1/4	252.0	169.0	48,900	107,600
60	2 1/2	303.5	203.5	59,000	129,800
65	2 5/8	355.0	238.0	68,300	150,300
70	2 3/4	409.5	274.6	78,400	172,600
75	3	469.5	314.8	87,900	193,300
80	3 1/4	533.5	357.7	100,900	222,000
85	3 3/8	602.5	404.0	113,300	249,300
90	3 1/2	679.5	455.6	126,700	278,700
95	3 3/4	761.0	510.3	141,100	310,400
100	4	838.0	561.9	154,400	339,800

Diameter, weight and MBS are determined in accordance with ISO 2307: 2019. Specifications are for unspliced strengths, strength will decrease by about 10% after splicing. Custom size and length and color available by request.

Warning: The minimum breaking strength must never be regarded as the safe working load of the rope.

Can be certified by



ROPEERS
RELIABLE TO THE CORE