OPTIMA 3 Winch Line

- ▶ Made with UHMWPE fiber, with high wear resistance and excellent tensile strength
- ► Coated with polyurethane for added UV resistance and chemical resistance
- Customizable in length and color

Application:







		Second States						
		and and a second	Diameter		Weight		Minimun Breaking Strength	
			inch	mm	lbs/100ft	kg/100m	lbs	kg
Contraction of the second	Sere Contractor	eesee	1/4	6	1.5	2.2	8,600	3,900
CCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCCC		erer and	5/16	8	2.3	3.4	13,200	6,000
		and the second	3/8	10	3.6	5.4	18,700	8,500
	are contraction	ered the	7/16	11	4.0	6.0	22,600	10,300
C. C.C.C.C.C.C.	erez a state	SP COM	1/2	12	6.4	9.5	31,500	14,300
	AL SAL	Lever Com	9/16	14	7.0	10.5	38,000	17,300
	All and all			16	10.3	15.4	51,700	23,500
	all		3/4	18	13.4	20.1	68,500	31,100
	al		7/8	22	18.8	28.0	92,200	41,900
			1	24	22.2	33.1	109,800	49,900
			1 1/16	26	25.7	38.4	130,000	59,100
			1 1/8	28	30.5	45.5	137,100	62,300
			1 1/4	30	33.9	50.6	154,200	70,100
			1 5/16	32	38.6	57.5	182,200	82,800
LIFE CONTRACTOR		The for the Part	1 1/2	36	48.3	72.0	205,500	93,400
		â.	1 5/8	40	59.0	88.0	256,300	116,500
			1 3/4	44	71.4	106.5	308,000	140,000
	DNV·GL	CENT L'ANNE	2	48	84.0	125.2	361,000	164,100
	ISO ISO9001		Specifications are for spliced strengths Custom size and length available by request					

Custom size and length available by request



ROPERS ROPE

□ sales@ropers.com.tw www.ropersrope.com

