















**UV** and chemical resistance



## **Technical Information**































Diameter	Weight	Minimun Breaking Strength	Minimum Strength ISO Unspliced Rope
inch	lbs/100ft	lbs	lbs
3/8	6.0	20,900	23,200
7/16	6.7	25,500	28,300
1/2	9.3	33,000	36,700
9/16	11.7	41,800	46,400
5/8	17.2	54,100	60,100
3/4	22.6	71,900	79,900
7/8	31.3	101,200	112,400
1	36.9	114,400	127,100
1 1/16	45.3	134,400	149,300
1 1/8	53.1	149,600	166,200
1 1/4	58.7	170,500	189,400
1 5/16	68.2	200,200	222,400
1 1/2	82.8	226,600	251,800
1 5/8	105.1	292,600	325,100
1 3/4	128.5	323,400	359,300
2	143.0	360,800	400,900
2 1/8	175.5	435,600	484,000

Diameter, weight and MBS are determined in accordance with CI1500-02. Custom size and length available by request.